

SUPER FILLER INDUSTRIES

KAOMAX INDUSTRIES

KAOTECH INDUSTRIES

PROCESSES KAOLIN LUMPS

Grade - Coating Clay (XL - 999)

Characteristics

Standard Specifications

Physical Properties

Brightness (ISO) %	85 ± 2
Moisture (W/W)%	< 8.00
pH (of 10 % suspension)	4.0 – 6.0

PSD

Particle Size < 2 μ	80-85%
-------------------------	--------

Sieve Residue

Retention % on 325# ASTM sieve	< 0.001
--------------------------------	---------

Chemical Composition

Al ₂ O ₃ %	38 – 40
Fe ₂ O ₃ %	< 0.1
Loss on Ignition	12.0 – 14.0

The figures given in the data sheet are mean representative values. Due to minerals being natural product, the specification in this data sheet may not be treated as warranty.

Head Office : 26, Tulsi Nagar, Hiran Magri Sec-5, Udaipur (Raj.)
 Units : Udaipur, Beawar, Bhuj.
 Phone Numbers : 9413317099, 9414254090, 7903113610
 E-mail us : superfiller@gmail.com